















Reactive dyes for dyeing cellulosic fiber & Blends. 50~60°C exhaustion dyeing, continuous dyeing and pad-batch dyeing.

Sunzol®	on Cotton	(%O.w.f.)	C.I.Reactive	Solubility	Light	Fastness		
						Washing	Rubbing	Chlorinated Water
Yellow GL		3.0	Y-37	100 40	6	5 5	5 4	4-5
Yellow GR 150%		2.0	Y-15	80 70	5	4-5 5	5 3	1-2
Yellow R		3.0	-	200 120	5	4-5 5	5 3	1
Yellow 2RN 150%		2.0	-	200 160	4-5	5 5	5 4	2
Brill. Orange 3R		3.0	O-16	90 30	4-5	5 5	5 3-4	2
Red BB 150%		2.0	R-21	140 80	4	5 4-5	5 3-4	1
Red RB 133%		3.0	R-198	200 200	4-5	5 4-5	5 3	2-3
Red 3B		3.0	R-23	100 50	6-7	5 5	5 4	5
Brill. Violet 5R		3.0	V-5	200 200	5	4-5 5	4-5 3-4	4-5
Turquoise Blue G %133 / %165 / % 266		2.4	B-21	200 200	5	4-5 3	5 2-3	1-2
Brill. Blue R Special 150%		2.0	B-19	200 200	5	5 5	5 3-4	2-3
Brill. Blue RS		2.0	B-19	200 200	5	5 5	5 3-4	2-3

[Türkçe Menü](#)